

**Dispersions of crosslinked polymer micro-particles in aqueous media, a process for the preparation of these dispersions, and coating compositions containing these dispersions**

Patent Number: ☐ US4945128  
Publication date: 1990-07-31  
Inventor(s): HILLE HANS-DIETER (DE); MULLER HORST (DE); DOBBELSTEIN ARNOLD (DE)  
Applicant(s):: BASF LACKE & FARBEN (DE)  
Requested Patent: ☐ EP0234361, B1, B2  
Application Number: US19880267126 19880826  
Priority Number(s): DE19863606512 19860228  
IPC Classification: C08G18/42 ; C08L75/06  
EC Classification: C08G18/08B6, C08G18/42F, C08G18/75B6C3  
Equivalents: BR8707620, CA1299309, ☐ DE3606512, ☐ EP0294376 (WO8705305), ES2014260T, JP1501869T, JP2697737B2, ☐ WO8705305

---

**Abstract**

---

PCT No. PCT/EP87/00056 Sec. 371 Date Aug. 26, 1988 Sec. 102(e) Date Aug. 26, 1988 PCT Filed Feb. 6, 1987 PCT Pub. No. WO87/05305 PCT Pub. Date Sep. 11, 1987. Dispersions of crosslinked polymer micro-particles in aqueous media, a process for the preparation of these dispersions, and coating compositions containing these dispersions. The invention relates to dispersions of crosslinked polymer micro-particles in aqueous media, which have been prepared: (1) by dispersing a mixture of the components (A) and (B) in an aqueous medium, the component (A) being composed of one or more polyester-polyols containing at least 2 hydroxyl groups, and the component (B) being composed of one or more polyisocyanate compounds, and the component (A) having available a number of ionic groups, preferably carboxylate groups, sufficient to form a stable dispersion, and at least one part of the components (A) and/or (B) containing more than 2 hydroxyl or isocyanate, respectively, groups per molecule and (2) by subsequently heating the dispersion thus obtained to a temperature sufficiently high for the components (A) and (B) to react to form crosslinked polymer micro-particles.

---

Data supplied from the esp@cenet database - I2